



Technical data sheet

Instant Adhesive

MD GLUE 150.424

08/04/2019

medium vis	scosity
------------	---------

NSF Registration No. 150265 Categorie Code: P1

Base	Ethyl Cyanacrylate
Color	transparent
Viscosity 25°C	50-100 mPa.s
Density	1,05 g/cm ³
Flashpoint	85°C
Setting time Aluminium	8-20 sec.
Setting Rubber	8-12 sec.
Final cure	24 h
Max. gap filling	0,07 mm
Temperature resistance	-60°C till +80°C
Thermal conductivity ASTM C 177	0,1
Tensile Shear Strength steel DIN 53283	22 N/mm²
Shelf life at 5°C till 8°C	12 months

The values are average values. They serve merely for your information, but assume no warranty.

REACH registriert

Not included in this product:

Amines, benzene, benzoyl, biocides, bisphenol, DEHP, peanut oil, halogen, latex, Nanoparticles, persistent, perluorierte surfactants, PFOA, PFOX, phthalates, silicone

Description to use:

The parts to be bonded must be clean, oil- and greasefree. Give MD GLUE thinly on one side and pressing parts together. To accelerate the curing, you can use MD ACTIVATOR NO. 9 No.9. To accelerate the curing of materials such as PP, PE, Teflon or silicone you can use our MD PRIMER NO. 7.

Bergheimer Str. 15 | D-53909 Zülpich | Tel. 02252/94150 | info@marston-domsel.de www.marston-domsel.de

The information in this product has been compiled to the best of our knowledge and is intended purely for information purposes. No claims can be inferred therefrom. Before use, thorough experiments should be carried out. Our brochure represents a basis. Responsibility for possible measures to protect property and persons lies with the user. Safety data sheets on the required standard are available for all products on request.

Technical data sheet



Instant Adhesive

MD GLUE 150.424 Instant adhesive	
+	
++	
+	
+	
+	
Universal, slight gap bridging	
+ suitable ++ ideal	
cool, dry, dark, optimum temperature 6°C to 8°C	

RoHS compliant

Item number
MGL.150.PT5
MGL.150.F10
MGL.150.F10-BK
MGL.150.F20
MGL.150.F50
MGL.150.F500
MGL.150.K20

Bergheimer Str. 15 | D-53909 Zülpich | Tel. 02252/94150 | info@marston-domsel.de www.marston-domsel.de

The information in this product has been compiled to the best of our knowledge and is intended purely for information purposes. No claims can be inferred therefrom. Before use, thorough experiments should be carried out. Our brochure represents a basis. Responsibility for possible measures to protect property and persons lies with the user. Safety data sheets on the required standard are available for all products on request.